



GENERAL PRODUCT SPECIFICATION

Item No.	RFO412
-----------------	---------------

Date	16-6-2017	Replaces	7-24-2009	No. Pages	1
-------------	-----------	-----------------	-----------	------------------	---

Product Description:

Style	SOC
Item Size (each)	7.6 cm d x 122 cm long
Color	White with blue logo printing
Composition	> 96% Cellulose, < 4% Spunbond
Structure	Sorbent fill: Micro-fibrous Cellulose Outer covering: Spunbond polypropylene nonwoven (15-30 micron dia. fiber)
Technology	Cellulose + Spunbond + Sealed or Enclosed Ends
Absorbency	Hydrophobic + Oleophilic

Intended Application	Sorbent Sock for Spills of Oil Base or Solvent Base Liquids. Not intended for aggressive fluids.
-----------------------------	--------------------------------------------------------------------------------------------------

Absorbency Capacity	67 l per case (saturated; medium viscosity- 13.5x)
----------------------------	----------------------------------------------------

Packaging Description:

Package configuration	Case	Pkg. Weight	5.3 kg (4.3 kg)
Items per Package	12 SOCS/Case	Pkg. Dimensions (approx.)	33 cm x 56 cm x 33 cm (H)
Container type	Carton		

Physical Properties;

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
SOC Weight	Gravimetric	kg	0.32	0.09
Absorbency** (med. oil)	SPCTM-012B	gL/gS	13.5	1.3
Color	Visual	-----	White	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.